



BENEFITS:

- Excellent adhesion to concrete,
- Very low shrinkage contributing to good dimension stability,
- High mechanical strength, both tensile and compressive,
- Resistance to oils, fuel, and many chemicals.
- Abrasion resistance.

PRODUCT DESCRIPTION:

FloorCEM EPU-2 is a high performance three component epoxy-polyurethane modified self-smoothing screed designed as surface topcoat.

USES:

Metal, wood, concrete and plastered floor surfaces in factories, warehouses, chemical plants, workshops, clean rooms, electrical/electronic and computer related industries, food processing areas, pharmaceuticals, railway coaches, service areas, etc.

PROPERTIES:

- Placing without joints in layers of 1-2 mm.
- High compressive strength
- Resistant to wear and abrasion
- Waterproof
- Crack-free
- Resistant against gasoline, diesel oil, mineral oil, freeze-thaw cycles and deicing salts.
- Shock resistant
- No dust formation

Pot Life at 30 °C: 30-60 minutes

Light traffic use: 24 hours

Compressive strength: > 50 N/mm²

Tensile strength: > 16 N/mm²

Bond Strength: >2.6 N/mm²

Foot Traffic: after 24 hrs.

Top coat Time: 2-3 days

PRODUCT SYSTEM:

1. Primer: **FloorPrime EP5104/EPW**
2. Midcoat: **FloorScreed EP5300**
3. Topcoat: **FloorCEM EPU-2**

APPLICATION DATA:

PREPARATION OF SUBSTRATE:

The substrate must be sound clean, and free of oil. Sandblasting is most effective. If, however, this not possible, vigorous wire-brushing or roughening with coarse emery paper may be resorted



to. Scarifying method should be another method for surface profile preparation. Degreasing with a solvent like acetone, benzene or toluene is then carried out.

APPLICATION:

The **FloorsPrime EP** is first applied on concrete surfaces as a primer.

FloorCEM EPU-2: Mixing of the component A and component B is carried out with an improvised mechanical mixer by using a drill motor, with suitable stirrer attached in place of drill bit. Component C is added to get flowable screed. Please refer separate '**Application Guideline for FloorCEM EPU-2**'. Apply material at 2 mm thickness.

For desired finishes, choose from suitable product range Floorkrete product range.

STORAGE AND HANDLING:

The material, when stored in their original containers and not exposed to undue heat or humidity as in outdoor open sheds, will have a minimum shelf life of 6 months. Store in dry, frost-free conditions at moderate temperatures not greater than 25 °C. As far as possible, direct contact mixed material with the skin should be avoided as they might cause irritation on sensitive skins. It is advisable to wash off the material immediately if it does come in contact with the skin.

PACKAGING AND COVERAGE:

Pack Size: 20 kg composite pack, coverage: 3.0 to 3.5 ft²/Kg for 2mm thickness, actual thickness will depend on surface trials at site.

CLEANING:

All tools should be cleaned with solvent immediately after use.

STORAGE:

Store in dry, frost-free conditions at moderate temperatures not greater than 25 °C.

WARRANTY

Multichem warrants **FloorCEM EPU-2** products to be free from manufacturing defects as defined in this warranty. Manufacturing defects are considered to be those defects that occur due to the quality of the ingredients or from the manufacturing process itself. This warranty does not include labor costs and other costs or expenses associated with the removal or installation of **FloorCEM EPU-2** Products.

Because the Multichem does not perform the actual installation, it cannot be held responsible for the results of the application. Multichem specifically disclaims problems that occur due to weather conditions, structural movement, structural design flaws and application techniques.

This warranty is in lieu of all other warranties expressed or implied including the warranty of merchantability and fitness of purpose and of all other obligations or liabilities on Multichem part. Multichem neither assumes nor authorizes any person to assume for Multichem any liability in connection with the sale and installation of **FloorCEM EPU-2** products.

Because of constant improvement of manufacturing techniques and formulations, Company reserves rights to change this datasheet and its contents without prior notice.